

Brick of Glass | グラソア

GLASSORE

Brick of Glass

GLASSORE

GlassOre — Constructs space with artistic light


Enriching your creativity with its multipurpose simplicity.
GlassOre, brick of glass, is characterized by its unique texture.
Its surface is rough like a rock that has been weathered for ages,
adjusted to its surroundings. The very moment GlassOre is lit up,
its expression changes dramatically.

光のドラマで、空間を構築する [グラソア]

粗い表面を持つレンガのような素材感と存在感。半透明のガラス塊を透る、美しく柔らかな光の表情。
ガラスレンガ「グラソア」は、様々なシチュエーションで。アーティスティックな光空間を演出します。



名古屋第二赤十字病院
〔愛知〕
設計/山下設計



医療法人 社団駿甲会
コミュニティホスピタル
甲賀病院
〔静岡〕
設計/類設計室



アースブリックス
〔千葉〕
設計/アトリエ・天工人



鳥良 上野駅前店
〔東京〕
設計/ビス・アティック



グランド・ハイアット福岡
BAR FIZZ
〔福岡〕
設計/スーパーポテト





竹下通り
〔東京〕
設計／アーバンデザイナーズ
アソシエイテッド

赤坂サカス
〔東京〕
設計／久米設計



万代シティ
〔新潟〕
設計／アーバンデザイナーズ
アソシエイテッド



LINE UP

BRICK [Size] 約100×200mm [Thickness] 約50mm [Weight] 2.3kg	VOA [Size] 約50×50×1000mm [Weight] 約5.9kg	BAN [Size] 約100×50×600mm [Weight] 約7.0kg
--	---	---

グラソア
〔乳白タイプ〕
やさしい乳白色が穏やかな表情をたたえる、白濁したガラス塊
[Milky-White]
Milky solid Glass, whose inward glass-crystals produce distinctive expression.



グラソア
〔半透明タイプ〕
細やかな気泡が閉じこめられた、透きとおったガラス塊
[Semi-Transparent]
Semi-transparent solid Glass, which contains numerous fine air-bubbles



グラソア
〔ブルー〕
光を透すとあかるいブルーの色彩が華やかにきらめくガラス塊
[Blue]
Blue solid Glass, which sends out plenty of glorious blue sparkle in light



ガラスレンガ グラソア ■ 性能データ Properties

項目 Subject	単位	試験結果	インターロッキングブロック JASS7 M101
密度 Density	10 ³ kg/m ³	2.34	—
吸水率 Water Absorption Rate	wt%	0.007 ~ 0.012	—
曲げ強度 Bending Strength	MPa	18	5以上
圧縮強さ Compression Strength	MPa	80*	32以上
耐摩耗性 Abrasion Strength	g	0.002 ~ 0.005**	—
滑り抵抗値 Slip Resistance	乾燥状態 Dry	85 ~ 91*	40以上
	湿潤状態 Wet	40 ~ 42**	

【設計・施工上の注意】
 ●グラソア、グラソア VOA、グラソア BAN の寸法には多少のばらつきがあります。
 ●製法上多少の偏肉があります。
 ●製品には透明度、色調、肉厚等、個体差がありますので、ご了承ください。
 ●表面側と側面側は粗面になっています。(表面側と側面側のテクスチャは若干異なります。)
 ●色調は本カタログとの色とは若干異なる場合がございますので、サンプルにてご確認ください。

[NOTICE]
 ・GlassOre, GlassOre VOA, and GlassOre BAN have some dimensional variance.
 ・The thickness is slightly uneven due to the manufacturing method.
 ・Products have individual differences in transparency, color tone, and thickness, among others.
 ・Surfaces except the base are rough.
 (The texture on the top surface is slightly different from that of the four sides.)
 ・Actual colors may be slightly different from this catalog.
 Please check actual colors with samples.

上記の数値は測定値であり、保証値ではありません。
 ※は財団法人全国タイル検査・技術協会岐阜試験室での測定値です。他の試験結果は社内測定値です。
 ※The above-mentioned numerical values are measured, not guaranteed.