

Brick of Glass | グラソア

# GLASSORE

Brick of Glass

GLASSORE

GlassOre — Constructs space with artistic light


Enriching your creativity with its multipurpose simplicity.  
GlassOre, brick of glass, is characterized by its unique texture.  
Its surface is rough like a rock that has been weathered for ages,  
adjusted to its surroundings. The very moment GlassOre is lit up,  
its expression changes dramatically.

## 光のドラマで、空間を構築する [ グラソア ]

粗い表面を持つレンガのような素材感と存在感。半透明のガラス塊を透る、美しく柔らかな光の表情。  
ガラスレンガ「グラソア」は、様々なシチュエーションで。アーティスティックな光空間を演出します。



名古屋第二赤十字病院  
〔愛知〕  
設計/山下設計



医療法人 社団駿甲会  
コミュニティホスピタル  
甲賀病院  
〔静岡〕  
設計/類設計室





アースブリックス  
〔千葉〕  
設計/アトリエ・天工人



鳥良 上野駅前店  
〔東京〕  
設計/ビス・アティック



グランド・ハイアット福岡  
BAR FIZZ  
〔福岡〕  
設計/スーパーポテト







竹下通り  
〔東京〕  
設計／アーバンデザイナーズ  
アソシエイテッド

赤坂サカス  
〔東京〕  
設計／久米設計



万代シティ  
〔新潟〕  
設計／アーバンデザイナーズ  
アソシエイテッド



**LINE UP**

**BRICK**  
[Size] 約100×200mm  
[Thickness] 約50mm  
[Weight] 2.3kg

**VOA**  
[Size] 約50×50×1000mm  
[Weight] 約5.9kg

**BAN**  
[Size] 約100×50×600mm  
[Weight] 約7.0kg

**グラソア  
〔乳白タイプ〕**  
やさしい乳白色が穏やかな表情をたたえる、白濁したガラス塊  
[Milky-White]  
Milky solid Glass, whose inward glass-crystals produce distinctive expression.



**グラソア  
〔半透明タイプ〕**  
細やかな気泡が閉じこめられた、透きとおったガラス塊  
[Semi-Transparent]  
Semi-transparent solid Glass, which contains numerous fine air-bubbles



**グラソア  
〔ブルー〕**  
光を透すとあかるいブルーの色彩が華やかにきらめくガラス塊  
[Blue]  
Blue solid Glass, which sends out plenty of glorious blue sparkle in light



**ガラスレンガ グラソア** ■ 性能データ Properties

項目 Subject	単位	試験結果	インターロッキングブロック JASS7 M101
密度 Density	10 <sup>3</sup> /kg/m <sup>3</sup>	2.34	—
吸水率 Water Absorption Rate	wt%	0.007 ~ 0.012	—
曲げ強度 Bending Strength	MPa	18	5以上
圧縮強さ Compression Strength	MPa	80*	32以上
耐摩耗性 Abrasion Strength	g	0.002 ~ 0.005**	—
滑り抵抗値 Slip Resistance	乾燥状態 Dry	85 ~ 91*	40以上
	湿潤状態 Wet	40 ~ 42**	

- 【設計・施工上の注意】**
- グラソア、グラソア VOA、グラソア BAN の寸法には多少のばらつきがあります。
  - 製法上多少の偏肉があります。
  - 製品には透明度、色調、肉厚等、個体差がありますので、ご了承ください。
  - 表面側と側面側は粗面になっています。(表面側と側面側のテクスチャは若干異なります。)
  - 色調は本カタログとの色とは若干異なる場合がございますので、サンプルにてご確認ください。

- [NOTICE]**
- GlassOre, GlassOre VOA, and GlassOre BAN have some dimensional variance.
  - The thickness is slightly uneven due to the manufacturing method.
  - Products have individual differences in transparency, color tone, and thickness, among others.
  - Surfaces except the base are rough. (The texture on the top surface is slightly different from that of the four sides.)
  - Actual colors may be slightly different from this catalog. Please check actual colors with samples.

上記の数値は測定値であり、保証値ではありません。  
\*は財団法人全国タイル検査・技術協会岐阜試験室での測定値です。他の試験結果は社内測定値です。  
\*\*The above-mentioned numerical values are measured, not guaranteed.